

Aws D 1 3 D 1 Structural Welding Code Sheet Steel

Aws D 1 3 D 1 Structural Welding Code www.whlarchitecture.com by Gretchen & Chace

INTRODUCTION TO AWS D1.3 / D1.3M: THE STRUCTURAL WELDING CODE FOR SHEET STEEL

When it comes to structural welding, few standards carry as much weight as the American Welding Society (AWS) codes. Among these, **AWS D1.3 / D1.3M - Structural Welding Code - Sheet Steel** (often referred to as "AWS D1.3 D1 Structural Welding Code Sheet Steel") is the definitive guide for welding sheet steel components used in load-bearing applications. While its more famous sibling, AWS D1.1, governs thick plate and structural shapes, D1.3 specifically addresses the unique challenges of welding sheet steel—typically material less than 1/8 inch (3 mm) thick.

Whether you are a welding engineer, a fabricator, a quality assurance manager, or a student of welding technology, understanding the AWS D1.3 code is essential for producing safe, reliable, and code-compliant sheet steel structures. This article provides a comprehensive walkthrough of the code's scope, key provisions, material requirements, qualification procedures, and practical applications. By the end, you will have a solid grasp of how to apply **AWS D1.3 D1 Structural Welding Code Sheet Steel** in real-world projects.

WHAT IS AWS D1.3 / D1.3M?

The AWS D1.3 code is part of the American Welding Society's D1 family of structural welding standards. The "D1.3" designation refers to the standard, while "D1.3M" denotes the metric version. The full title—*Structural Welding Code - Sheet Steel*—clearly defines its scope: it covers the welding of sheet steel materials (typically carbon and low-alloy steels) that are 0.0625 inch (1.6 mm) to 0.1875 inch (4.8 mm) in thickness. However, the code can also be applied to thinner materials when specific provisions are met.

The code provides requirements for:

- Design of welded connections
- Welding procedure qualification
- Welder and welding operator qualification
- Fabrication and erection
- Inspection and testing

While AWS D1.1 dominates the heavy structural steel industry, **AWS D1.3 D1 Structural Welding Code Sheet Steel** fills a critical niche for sheet metal fabricators, automotive frame builders, light steel frame manufacturers, and HVAC ductwork producers. It ensures that even the thinnest steel components can be welded with the same level of rigor expected in heavy construction.

KEY DIFFERENCES BETWEEN AWS D1.3 AND AWS D1.1

Many professionals ask: "Why can't I just use D1.1 for sheet steel?" The answer lies in the fundamental differences in material behavior and welding response. Sheet steel is more prone to distortion, burn-through, and heat-affected zone (HAZ) softening. The AWS D1.3 code addresses these issues directly. Here are the

primary distinctions:

Thickness Range

- **AWS D1.1:** Typically for material 1/8 inch (3 mm) and thicker, with separate provisions for thinner material in some cases.
- **AWS D1.3:** Explicitly designed for sheet steel thicknesses from 0.0625 to 0.1875 inches (1.6 to 4.8 mm), with extensions to 0.25 inches (6 mm) under certain conditions.

Welding Processes

D1.3 emphasizes processes that minimize heat input and distortion, such as gas metal arc welding (GMAW) and flux-cored arc welding (FCAW) using short-circuiting transfer. While D1.1 also covers these processes, D1.3 provides specific guidance on parameters to avoid excessive melting or warping.

Joint Design

The code includes joint designs tailored for sheet steel—such as lap joints, corner joints, and edge flanging—which are less common in heavy structural work. Detailed tolerances and fit-up requirements prevent excessive gap that could lead to burn-through.

Qualification Testing

For D1.3, welder qualification tests use thinner test plates and specific bend test requirements that evaluate the weld's ability to withstand deformation without cracking. Visual and NDT criteria are also adapted for the thinner cross-section.

SCOPE AND APPLICABILITY OF THE CODE

AWS D1.3 is intended for welded structures made from sheet steel that are:

- Statically loaded or cyclically loaded (fatigue)
- Used in building frames, bridges (light pedestrian or vehicular), towers, storage racks, and other fabricated assemblies
- Manufactured from carbon steel grades typically ASTM A36, A1008, A1011, A653 (galvanized), and similar materials

The code explicitly does **not** cover: pressure vessels (covered by ASME codes), piping, or sheet steel less than 0.0625 inches unless specifically agreed upon by the engineer. It also does not supersede more stringent contract specifications.

MATERIAL REQUIREMENTS IN AWS D1.3

To achieve a code-compliant weld, the base metal must meet certain standards. The AWS D1.3 code references ASTM specifications for sheet steel. Commonly allowed materials include:

- **ASTM A36 / A36M** - Carbon structural steel (often in thicknesses that overlap the code's upper limit)
- **ASTM A1008 / A1008M** - Steel sheet, cold-rolled, carbon,

structural

- **ASTM A1011 / A1011M** – Hot-rolled carbon steel sheet
- **ASTM A653 / A653M** – Galvanized steel sheet (with appropriate welding precautions for zinc coatings)

Additionally, welding consumables (electrodes, wires, fluxes) must conform to AWS filler metal specifications such as A5.18 (ER70S-6 for GMAW) or A5.20 (E71T-11 for FCAW). The code also includes guidance on preheat and interpass temperatures when welding galvanized or coated steels—critical to avoid hydrogen-induced cracking and zinc fume exposure.

WELDING PROCEDURE SPECIFICATIONS (WPS) AND QUALIFICATION

Every project governed by **AWS D1.3 D1 Structural Welding Code Sheet Steel** requires a written Welding Procedure Specification (WPS) that has been qualified either by pre-qualification (if permitted) or by testing. Pre-qualified joints are those where the code provides ready-to-use parameters (e.g., specific joint geometries, thicknesses, and process variables) without the need for destructive testing. However, many sheet steel applications fall outside pre-qualified limits, so procedure qualification is common.

Key Variables in a D1.3 WPS

- Welding process (GMAW, FCAW, GTAW, SMAW—though shielded metal arc is less common on sheet)
- Base metal specification and thickness range
- Filler metal classification and diameter
- Joint design (lap, butt, T-joint, corner, edge)
- Welding position (flat, horizontal, vertical, overhead)
- Electrical parameters (voltage, amperage, travel speed, wire feed speed)
- Shielding gas composition and flow rate
- Preheat and interpass temperature (if applicable)

Qualification involves making test welds that are subjected to guided bend tests, macro-etch examination, and often tensile tests. The test results must meet the acceptance criteria outlined in the code—namely, no cracks, no incomplete fusion, and bend specimens must not show defects longer than 1/8 inch.

WELDER AND WELDING OPERATOR QUALIFICATION

Even with a qualified WPS, the person holding the torch must be individually qualified to perform the work. Under D1.3, welders are tested on a production-representative joint in a specific position (e.g., 2G, 3G, 4G for groove welds; 1F, 2F for fillet welds). The test plate thickness must match the range of sheet steel to be welded on the job.

Qualification tests for welders include:

- Visual inspection (convexity, undercut, porosity, overlap)
- Guided bend tests (transverse side bends for groove welds)
- Macro-etch examination (for fillet welds to assess penetration and fusion)

Successful welders receive a qualification record (WPQ) that is valid indefinitely unless the welder goes six months without using the specific process, or if there is specific reason to doubt their ability (e.g., a production failure).

INSPECTION AND ACCEPTANCE CRITERIA

Quality control in sheet steel welding demands a balanced approach: too little inspection risks failure, yet overly stringent criteria can reject acceptable welds. The AWS D1.3 code provides clear acceptance standards for both visual and nondestructive testing.

Visual Inspection (VT)

All welds must be visually examined. Key criteria:

- No cracks (no acceptance allowed)
- No incomplete fusion or incomplete joint penetration
- Undercut limited to 0.01 inches (0.3 mm) deep for sheet steel
- Porosity – individual pores not exceeding 1/16 inch (1.6 mm) diameter, and cumulative porosity not exceeding 2% of weld surface area
- Convexity and reinforcement height within specified limits

Nondestructive Testing (NDT)

When required by the contract or engineer, NDT methods like liquid penetrant testing (PT) or magnetic particle testing (MT) are used. Radiography (RT) is less common due to the thin gauge, but ultrasonic testing (UT) is sometimes applied using special couplants and transducers designed for thin sections.

Destructive Testing

Procedure qualification relies on destructive tests as noted above. For production welds, the code allows for random macro-etch sampling if agreed upon—a cost-effective way to verify consistency.

APPLICATIONS OF AWS D1.3 IN INDUSTRY

The scope of **AWS D1.3 D1 Structural Welding Code Sheet Steel** extends across many sectors. Understanding these applications helps you appreciate why this code is so vital.

Light Structural Steel Framing

Cold-formed steel (CFS) framing for commercial and residential buildings uses sheet steel from 12 gauge to 20 gauge. Welded connections—such as beam-to-column joints, truss splices, and bracing—must comply with D1.3 to ensure structural integrity under wind and seismic loads.

Storage Racks and Material Handling

Industrial pallet racks, cantilever racks, and shelving systems rely on welded sheet steel components. The code governs the welds on uprights, beams, and braces to prevent collapse under dynamic loads.

Automotive and Trailer Manufacturing

While automotive welding often follows its own standards (e.g., AWS D8.8 for sheet steel in automotive), many trailer frames, truck body panels, and agricultural equipment components are welded per D1.3, especially when the designer wants a

universally recognized structural code.

HVAC and Sheet Metal Ductwork

High-pressure ductwork and supporting frames sometimes require structural welds that exceed simple sheet metal screws. D1.3 provides